


UP 5690


VACUUM CASTING POLYURETHANE FOR TECHNICAL PARTS AND PROTOTYPES


	MECHAN	ICAL PROPE	ERTIES at 23	°C ⁽¹⁾		
A/B/C			100/100/0	100/100/20	100/100/30	100/100/50
Hardness	ISO 868 : 2003	Shore D	83	80	78	75
Tensile strength	ISO 527 : 1993	MPa	35	30	28	25
Flexural strength	ISO 178 : 2001	MPa	50	35	30	20
Flexural modulus	ISO 178 : 2001	MPa	1300	1000	900	600
Elongation at break	ISO 527 : 1993	%	50	60	65	90
Impact strength (CHARPY) Unnotched specimens	ISO 179/2D : 1994	KJ/m²	100	90	85	75


THERM	AL AND SPE	CIFIC PROPER	TIES		
A/B/C		100/100/0	100/100/20	100/100/30	100/100/50
Glass transition temperature (Tg) (1) .	°C	In process	In process	In process	In process
Linear shrinkage	%	0.35	0.35	0.35	0.35
Demoulding time (2 - 3mm) at 70°C	min		60	- 90	

(1): Average values obtained on standard specimens / Hardening 16hr at 80°C after demoulding.









Page 2/ 2- 26 Dec. 2008

AXSON France BP 40444 95005 Cergy Cedex FRANCE Tel. (33) 134403460 Fax (33) 134219787 Email : axson@axson.fr

AXSON GmbH Dietzenbach Tel. (49) 6074407110

AXSON Italie Saronno Tel. (39) 0296702336 AXSON IBERICA Barcelona Tel. (34) 932251620

AXSON UK Newmarket Tel. (44)1638660062 AXSON ASIA Seoul Tel. (82) 25994785


AXSON MEXICO Mexico DF Tel. (52) 5552644922 AXSON JAPAN OKAZAKI CITY Tel.(81)564262591


AXSON NA USA Eaton Rapids Tel. (1) 5176638191 AXSON SHANGHAI
Zip: 200131
Shanghai
Tel. (86) 58683037
Fax. (86) 58682601
E-mail: shanghai@axson.cn
Web: http://www.axson.com.cn



UP 5690

VACUUM CASTING POLYURETHANE FOR TECHNICAL PARTS AND PROTOTYPES





HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products:

Ensure good ventilation

Wear gloves, safety glasses and protective clothes.

For further information, please consult the product safety data sheet.

STORAGE CONDITIONS

Shelf life is 6 months in a dry place and in original unopened containers at a temperature between 15 and 25° C. Any open can must be tightly closed under dry nitrogen blanket.

PACKAGING

LID ECON AMIDIO 201/41414VIIII	UD 5000 AK/D/O 0 /4 / 4 / 11
UP 5690 AW/B/C 2x(1+1+1)kg	UP 5690 AK/B/C 2x(1+1+1)kg

GUARANTEE

The information of our technical data sheet are based on our present knowledge and the result of tests conducted under precise conditions. It is the responsibility of the user to determine the suitability of AXSON products, under their own conditions before commencing with the proposed application. AXSON refuse any guarantee about the compatibility of a product with any particular application. AXSON disclaim all responsibility for damage from any incident which results from the use of these products. The guarantee conditions are regulated by our general sale conditions.

Page 3/ 2- 26 Dec. 2008

AXSON France BP 40444 95005 Cergy Cedex FRANCE Tel. (33) 134403460 Fax (33) 134219787 Email: axson@axson.fr AXSON GmbH Dietzenbach Tel. (49) 6074407110

AXSON Italie Saronno Tel. (39) 0296702336 AXSON IBERICA Barcelona Tel. (34) 932251620

AXSON UK Newmarket Tel. (44)1638660062 AXSON ASIA Seoul Tel. (82) 25994785

AXSON MEXICO Mexico DF Tel. (52) 5552644922 AXSON JAPAN OKAZAKI CITY Tel.(81)564262591

AXSON NA USA Eaton Rapids Tel. (1) 5176638191 AXSON SHANGHAI Zip: 200131 Shanghai Tel. (86) 58683037 Fax. (86) 58682601. E-mail: shanghai@axson.cn Web: http://www.axson.com.cn